This listing of claims will replace all prior versions, and listings of claims in the application

Listing of Claims:

Claims 1-6. (Cancelled)

Claim 7. (Currently Amended) A polyurethane composition which cross-links via silane polycondensation and comprises

A) at least one alkoxysilane-functional polyurethane having end groups corresponding to formula (I)



(I),

wherein

R^1 represents an organic group having 1 to 12 carbon atoms,

n is an integer from 2 to 4 and

X, Y, Z represent identical or different organic groups, provided that at least one of the groups is an alkoxy group having 1 to 4 carbon atoms,

B) at least one ~~basic~~ filler,

C) at least one reaction product of

i) at least one aminosilane corresponding to formula (II)



(II),

wherein

R^2 represents a hydrogen atom or an aminoethyl group

n is 3 and

~~n,~~ X, Y, Z have the meanings set forth for formula (I),

with

ii) at least one maleic or fumaric ester corresponding to formula (III)

$$R_3OOC\text{-}CH{=}CH\text{-}COOR_3 \quad \text{(III)},$$

wherein

R_3 represents an alkyl group having 1 to 12 carbon atoms, and

D) at least one organometallic compound.

Claim 8. (Previously Presented) The polyurethane composition of Claim 7 wherein R_1 represents a group corresponding to formula (IIb)



(IIb),

wherein R_4 denotes an alkyl group having 1 to 4 carbon atoms.

Claim 9. (Previously Presented) The polyurethane composition of Claim 7 wherein component C) comprises an aminosilane compound corresponding to formula (V)



(V),

wherein

R_3 represents a linear or branched aliphatic hydrocarbon group having at most 12 carbon atoms,

n is 3 and

X, Y and Z represent methoxy or ethoxy groups.

Claim 10. (Previously Presented) The polyurethane composition of Claim 7 wherein X, Y and Z each represent a methoxy or ethoxy group.

Claim 11. (Previously Presented) The polyurethane composition of Claim 8 wherein X, Y and Z each represent a methoxy or ethoxy group.

Claim 12. (Previously Presented) The polyurethane composition of Claim 9 wherein X, Y and Z each represent a methoxy or ethoxy group.

Claim 13. (Previously Presented) The polyurethane composition of Claim 7 wherein X, Y and Z each represent a methoxy group in component A).

Claim 14. (Previously Presented) The polyurethane composition of Claim 8 wherein X, Y and Z each represent a methoxy group in component A).

Claim 15. (Previously Presented) The polyurethane composition of Claim 9 wherein X, Y and Z each represent a methoxy group in component A).

Claim 16. (Currently Amended) A process for the preparation of the polyurethane composition of Claim 1 which comprises mixing components A), B), ~~C-i)~~ and E) with exclusion of moisture and subsequently adding component C, the reaction product of i) and ii).

Claim 17. (New) A polyurethane composition which cross-links via silane polycondensation and comprises

A) at least one alkoxysilane-functional polyurethane having end groups corresponding to formula (I)



(I),

wherein

R^1 represents a group corresponding to formula (IIb)



(IIb),

wherein R_4 represents an ethyl group.

n is 3 and

X, Y, Z represent methoxy or ethoxy groups.

B) at least one filler,

C) at least one reaction product of

i) at least one aminosilane corresponding to formula (II)



(II),

wherein

R^2 represents an aminoethyl group and

n, X, Y, Z have the meanings set forth for formula (I),

with

ii) at least one maleic or fumaric ester corresponding to formula (III)

$$R_3OOC\text{-}CH{=}CH\text{-}COOR_3 \quad \text{(III)},$$

wherein

R_3 represents an alkyl group having 1 to 12 carbon atoms, and

D) at least one organometallic compound.